

平成27年度～令和2年度 溶融メタル分析試験測定結果表

年度	H27年度		H28年度		H29年度		H30年度		H31年度 (R元年度)		R2年度		年度	最小	最大	平均 (H27～ R2)
	6/8	12/3	6/9	1/6	6/9	12/8	7/9	3/11	7/3	1/8	8/5	1/7				
採取日	6/30	1/5	7/4	2/8	7/13	1/25	8/13	3/27	7/31	2/10	9/4	2/10	報告日			
鉄	78.30%	71.90%	68.40%	75.50%	69.20%	70.00%	67.10%	78.90%	71.80%	70.10%	69.30%	80.00%	鉄	67.10%	80.00%	72.54%
銅	7.60%	12.30%	11.00%	7.52%	16.00%	11.90%	12.30%	9.87%	13.70%	11.60%	12.10%	14.20%	銅	7.52%	16.00%	11.67%
ケイ素	4.00%	4.46%	5.77%	0.37%	1.63%	4.40%	4.04%	1.21%	1.18%	1.59%	4.58%	1.69%	ケイ素	0.37%	5.77%	2.91%
鉛	0.04%	0.13%	0.17%	0.02%	6.16%	0.26%	0.42%	0.20%	0.30%	0.21%	0.21%	0.13%	鉛	0.02%	6.16%	0.69%
金	<0.01%	0.01%	0.02%	<0.01%	0.02%	0.01%	0.01%	0.01%	<0.01%	<0.01%	<0.01%	<0.01%	金	<0.01%	0.02%	
銀	0.01%	<0.01%	<0.01%	<0.01%	0.01%	<0.01%	0.01%	0.01%	0.01%	<0.01%	<0.01%	0.02%	銀	<0.01%	0.02%	
亜鉛	0.14%	0.15%	0.20%	0.22%	0.99%	0.22%	0.14%	0.37%	0.26%	0.36%	0.24%	0.31%	亜鉛	0.14%	0.99%	0.30%
クロム	0.92%	1.54%	2.01%	1.35%	2.13%	1.93%	2.39%	1.07%	2.33%	1.08%	2.33%	0.44%	クロム	0.44%	2.39%	1.63%
マンガン	0.70%	0.96%	1.76%	0.44%	0.94%	1.23%	1.36%	0.67%	1.58%	0.36%	1.04%	0.25%	マンガン	0.25%	1.76%	0.94%
チタン	0.64%	1.08%	0.94%	0.03%	0.55%	1.12%	1.12%	0.22%	0.98%	0.26%	0.82%	0.04%	チタン	0.03%	1.12%	0.65%
ニッケル	0.81%	1.02%	1.22%	1.05%	1.03%	1.11%	1.38%	0.91%	1.42%	1.02%	1.44%	0.92%	ニッケル	0.81%	1.44%	1.11%
スズ	0.17%	0.26%	0.23%	0.14%	1.02%	0.32%	0.34%	0.26%	0.40%	0.25%	0.32%	0.32%	スズ	0.14%	1.02%	0.34%
リン	6.00%	7.67%	6.88%	6.45%	5.34%	7.90%	5.97%	6.36%	6.06%	6.16%	5.99%	4.39%	リン	4.39%	7.90%	6.26%
パラジウム	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	パラジウム	<0.01%	<0.01%	<0.01%
白金	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	白金	<0.01%	<0.01%	<0.01%