

平成30年度～令和4年度 溶融メタル分析試験測定結果表

年度	H30年度		H31年度 (R元年度)		R2年度		R3年度		R4年度		年度	最小	最大	平均
	採取日	7/9	3/11	7/3	1/8	8/5	1/7	7/6	1/6	7/21	2/2			
報告日	8/13	3/27	7/31	2/10	9/4	2/10	8/3	2/15	8/23	3/7	報告日			
鉄	67.10%	78.90%	71.80%	70.10%	69.30%	80.00%	78.30%	59.50%	64.10%	70.40%	鉄	59.50%	80.00%	70.95%
銅	12.30%	9.87%	13.70%	11.60%	12.10%	14.20%	8.80%	26.60%	13.40%	12.90%	銅	8.80%	26.60%	13.55%
ケイ素	4.04%	1.21%	1.18%	1.59%	4.58%	1.69%	1.02%	1.28%	2.93%	3.84%	ケイ素	1.02%	4.58%	2.34%
鉛	0.42%	0.20%	0.30%	0.21%	0.21%	0.13%	0.10%	1.76%	0.57%	0.67%	鉛	0.10%	1.76%	0.46%
金	0.01%	0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	金	0.01%	0.01%	0.01%
銀	0.01%	0.01%	0.01%	<0.01%	<0.01%	0.02%	0.01%	0.14%	0.03%	0.07%	銀	0.01%	0.14%	0.04%
亜鉛	0.14%	0.37%	0.26%	0.36%	0.24%	0.31%	0.26%	1.06%	0.37%	0.31%	亜鉛	0.14%	1.06%	0.37%
クロム	2.39%	1.07%	2.33%	1.08%	2.33%	0.44%	1.01%	2.00%	1.46%	1.60%	クロム	0.44%	2.39%	1.57%
マンガン	1.36%	0.67%	1.58%	0.36%	1.04%	0.25%	0.47%	0.54%	0.79%	0.93%	マンガン	0.25%	1.58%	0.80%
チタン	1.12%	0.22%	0.98%	0.26%	0.82%	0.04%	0.12%	0.04%	0.96%	0.72%	チタン	0.04%	1.12%	0.53%
ニッケル	1.38%	0.91%	1.42%	1.02%	1.44%	0.92%	0.99%	1.42%	1.09%	1.13%	ニッケル	0.91%	1.44%	1.17%
スズ	0.34%	0.26%	0.40%	0.25%	0.32%	0.32%	0.20%	1.07%	0.44%	0.57%	スズ	0.20%	1.07%	0.42%
リン	5.97%	6.36%	6.06%	6.16%	5.99%	4.39%	6.19%	3.57%	6.50%	6.33%	リン	3.57%	6.50%	5.75%
パラジウム	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	パラジウム	<0.01%	<0.01%	<0.01%
白金	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	<0.01%	白金	<0.01%	<0.01%	<0.01%